

Serial No. 10/526,771

IN THE CLAIMS:

1. (Currently Amended) A modified propylene based polymer satisfying the following (1) to (4):

(1) the content of polar group moieties resulting from a compound containing in the same molecule thereof an ethylenic double bond and a polar group is from 0.10 to 0.30 mmol/g,

(2) the intrinsic viscosity ($[\eta]_A$) measured at 135°C in tetralin is from 0.8 to 3.0 dl/g,

(3) the molecular weight distribution (M_w/M_n) is more than 2.5, and

(4) the content of components in the modified propylene based polymer having a molecular weight (M_w) of 10,000 or less is 5% or less by weight.

2. (Currently Amended) The modified propylene based polymer according to claim 1, wherein the ratio of the intrinsic viscosity ($[\eta]_A$) thereof to the intrinsic viscosity ($[\eta]_S$) of a propylene based polymer ~~which~~ that is a starting material of the modified polymer ($[\eta]_A/[\eta]_S$) is 0.2 or more.

Serial No. 10/526,771

3. (Original) The modified propylene based polymer according to claim 1, wherein the compound containing in the same molecule thereof an ethylenic double bond and a polar group is an unsaturated carboxylic acid and/or a derivative thereof.

4. (Currently Amended) A process for producing the modified propylene based polymer according to claim 1, which comprises blending a propylene based polymer, a radical initiator, and a compound containing in the same molecule thereof an ethylenic double bond and a polar group; and melting and kneading the resultant at a temperature of not lower than the melting point of the propylene based polymer and less than 180°C or less.

5. (Original) A polyolefin resin composition comprising the following (A), (B) and (C), or the following (A), (B), (C) and (D):

- (A) a polymer synthesized from an α -olefin having 3 or more carbon atoms,
- (B) the modified propylene based polymer according to claim 1,
- (C) an organized layer inorganic compound, and
- (D) a rubbery polymer.

Serial No. 10/526,771

6. (Original) A polyolefin resin composition comprising the following (A), (B) and (C), or the following (A), (B), (C) and (D);

(A) a polymer synthesized from an α -olefin having 3 or more carbon atoms,

(B) the modified propylene based polymer according to claim 2,

(C) an organized layer inorganic compound, and

(D) a rubbery polymer.

7. (Original) A polyolefin resin composition comprising the following (A), (B) and (C), or the following (A), (B), (C) and (D);

(A) a polymer synthesized from an α -olefin having 3 or more carbon atoms,

(B) the modified propylene based polymer according to claim 3,

(C) an organized layer inorganic compound, and

(D) a rubbery polymer.

8. (Currently Amended) The polyolefin resin composition according to claim 5, wherein the melt flow rate of the α -olefin polymer (A) is from 0.1 to 200 g/10-minutes, and the α -olefin polymer (A) is a homopolymer or a copolymer of a

Serial No. 10/526,771

first α -olefin ~~which~~ that has 3 or more carbon atoms and 0 to 20% by weight of a second α -olefin in ~~which~~ that is different from the first α -olefin and has 2 to 20 carbon atoms.

9. (Original) A process for producing the polyolefin resin composition according to claim 5, which comprises blending the (A), (B) and (C), or the (A), (B), (C) and (D); and then melting and kneading the resultant.

10. (New) A propylene based polymer modified only with a compound containing in the same molecule thereof an ethylenic double bond and a polar group, the modified polymer satisfying the following (1) to (4):

- (1) the content of polar group moieties resulting from the compound containing in the same molecule thereof an ethylenic double bond and a polar group is from 0.10 to 0.30 mmol/g,
 - (2) the intrinsic viscosity ($[\eta]$) measured at 135°C in tetralin is from 0.8 to 3.0 dl/g,
 - (3) the molecular weight distribution (M_w/M_n) is more than 2.5,
- and

Serial No. 10/526,771

(4) the content of components in the modified polymer having a molecular weight (Mw) of 10,000 or less is 5% or less by weight.

11. (New) The modified propylene based polymer according to claim 10, wherein the ratio of the intrinsic viscosity ($[\eta]A$) thereof to the intrinsic viscosity ($[\eta]B$) of a propylene based polymer that is a starting material of the modified polymer ($[\eta]A/([\eta]B)$ is 0.2 or more.

12. (New) The modified propylene based polymer according to claim 10, wherein the compound containing in the same molecule thereof an ethylenic double bond and a polar group is an unsaturated carboxylic acid and/or a derivative thereof.

13. (New) A process for producing the modified propylene based polymer according to claim 10, which comprises blending a propylene based polymer, a radical initiator, and a compound containing in the same molecule thereof an ethylenic double bond and a polar group; and melting and kneading the resultant at a temperature of not lower than the melting point of the propylene based polymer and 180°C or less.

Serial No. 10/526,771

14. (New) A polyolefin resin composition comprising the following (A), (B) and (C), or the following (A), (B), (C) and (D);

(A) a polymer synthesized from an α -olefin having 3 or more carbon atoms,

(B) the modified propylene based polymer according to claim 10,

(C) an organized layer inorganic compound, and

(D) a rubbery polymer.

15. (New) A polyolefin resin composition comprising the following (A), (B) and (C), or the following (A), (B), (C) and (D);

(A) a polymer synthesized from an α -olefin having 3 or more carbon atoms,

(B) the modified propylene based polymer according to claim 11,

(C) an organized layer inorganic compound, and

(D) a rubbery polymer.

16. (New) A polyolefin resin composition comprising the following (A), (B) and (C), or the following (A), (B), (C) and (D);

Serial No. 10/526,771

- (A) a polymer synthesized from an α -olefin having 3 or more carbon atoms,
- (B) the modified propylene based polymer according to claim 12,
- (C) an organized layer inorganic compound, and
- (D) a rubbery polymer.

17. (New) The polyolefin resin composition according to claim 14, wherein the melt flow rate of the α -olefin polymer (A) is from 0.1 to 200 g/10-minutes, and

the α -olefin polymer (A) is a homopolymer or a copolymer of a first α -olefin that has 3 or more carbon atoms and 0 to 20% by weight of a second α -olefin that is different from the first α -olefin and has 2 to 20 carbon atoms.

18. (New) A process for producing the polyolefin resin composition according to claim 14, which comprises blending the (A), (B) and (C), or the (A), (B), (C) and (D); and then melting and kneading the resultant.

19. (New) A polyolefin resin composition consisting essentially of the following (A), (B) and (C), or the following (A), (B), (C) and (D):

Serial No. 10/526,771

- (A) a polymer synthesized from an α -olefin having 3 or more carbon atoms,
- (B) the modified propylene based polymer according to claim 1,
- (C) an organized layer inorganic compound, and
- (D) a rubbery polymer.

20. (New) The polyolefin resin composition according to claim 19, wherein the melt flow rate of the α -olefin polymer (A) is from 0.1 to 200 g/10-minutes, and

the α -olefin polymer (A) is a homopolymer or a copolymer of a first α -olefin that has 3 or more carbon atoms and 0 to 20% by weight of a second α -olefin that is different from the first α -olefin and has 2 to 20 carbon atoms.

21. (New) A process for producing the polyolefin resin composition according to claim 19, which comprises blending the (A), (B) and (C), or the (A), (C), (C) and (U); and then melting and kneading the resultant.